

## INDUCTION FILMS & COATINGS Automotive Window Films

Product	Color	Thickness	Visible Light Transmission (VLT)	UV Rejection	Glare Reduction	Total Solar Energy Rejected	Infrared Rejection*	Glare Reduction
Jet Black								
Jet Black 5	Black	1.5 mils	5%	99%	95%	45%	27%	93%
Jet Black 15	Black	1.5 mils	16%	99%	82%	41%	26%	82%
Jet Black 20	Black	1.5 mils	22%	99%	78%	42%	26%	79%
Jet Black 30	Black	1.5 mils	32%	99%	65%	36%	26%	67%
Jet Black 35	Black	1.5 mils	34%	99%	62%	36%	26%	62%
Jet Black 43	Black	1.5 mils	43%	99%	53%	33%	26%	57%
Jet Black 50	Black	1.5 mils	51%	99%	45%	29%	26%	51%
Jet Black 55	Black	1.5 mils	55%	99%	40%	29%	26%	46%
Jet Black 70	Black	1.5 mils	70%	99%	23%	24%	26%	40%
Jet Black 88	Black	1.5 mils	86%	99%	39%	27%	58%	40%
Hybrid Ore								
Hybrid Ore 5	Black	1.5 mils	4%	99%	96%	59%	42%	94%
Hybrid Ore 15	Black	1.5 mils	13%	99%	86%	53%	41%	89%
Hybrid Ore 20	Black	1.5 mils	17%	99%	82%	53%	40%	78%
Hybrid Ore 35	Black	1.5 mils	34%	99%	63%	49%	42%	69%
Hybrid Ore 50	Black	1.5 mils	54%	99%	41%	36%	42%	57%
Ceramic								
Ceramic 5	Black	1.5 mils	5%	99%	95%	66%	85%	96%
Ceramic 15	Black	1.5 mils	14%	99%	83%	65%	85%	80%
Ceramic 20	Black	1.5 mils	20%	99%	78%	64%	85%	65%
Ceramic 30	Black	1.5 mils	30%	99%	67%	58%	85%	58%
Ceramic 35	Black	1.5 mils	36%	99%	60%	59%	85%	54%
Ceramic 45	Black	1.5 mils	46%	99%	50%	52%	83%	49%
Ceramic 55	Black	1.5 mils	54%	99%	41%	50%	84%	44%
Ceramic 70	Black	1.5 mils	68%	99%	27%	49%	89%	24%

\*Infrared Rejection as measured at 900-1,000 nm.

All values are as applied to 1/8" (3mm) clear glass.

The performance data reported was tested using ASHRAE, ASTM, and AIMCAL Standards.

